

# Desothane<sup>®</sup> HS CA8100 Series Military and Defense Anti-Chafe Topcoats

## TECHNICAL DATA SHEET

### Product Description

Desothane<sup>®</sup> HS CA8100 series military and defense anti-chafe topcoats are Teflon-filled polyurethanes. These topcoats are primarily used on surfaces where abrasion resistance, low friction, and impact resistance is required to reduce chafing and wear.

- Excellent gloss and color retention
- Compatible with Desoprime™ HS primers
- Excellent fluid resistance
- Compatible with all current spray equipment
- Can be applied in a wide range of conditions
- Service temperature -54°C to 177°C (-65°F to 350°F)

### Components



#### Mix ratio (by volume) for gloss colors:

- CA8100/XXXX (base component) 1 part
- CA8100 (activator component) 1 part

### Specifications



CA8100 series topcoats are qualified to the following material specifications:

- GC130RJ

CA8100 series topcoats are listed on the following process standard:

- PS 13555

*Note: PPG Aerospace recommends you check the most recent process standard for updated information.*

#### Product Compatibility:

CA8100 topcoats are compatible with the following primer and topcoat specifications:

- |                                |                 |
|--------------------------------|-----------------|
| • BMS 10-11 Type I             | • MIL-PRF-23377 |
| • BMS 10-60 Type I & Type II   | • MIL-PRF-85285 |
| • BMS 10-72 Type VIII          | • MIL-PRF-85582 |
| • BMS 10-79 Type II & Type III | • MMS 415       |
| • DMS 1786                     | • MMS 420       |
| • DMS 2104                     | • MMS 423       |
| • DMS 2115                     | • MMS 425       |
| • DMS 2144                     | • TT-P-2760     |

# Desothane<sup>®</sup> HS CA8100 Series Military and Defense Anti-Chafe Topcoats

## Surface Preparation and Pretreatments



CA8100 anti-chafe topcoats can be applied over clean, dry, intact epoxy primers, urethane primer, or polyurethane topcoats. They may be applied over primer or topcoat with no abrasion step if the coating was applied between 4 and 48 hours earlier. If it is longer than 48 hours, abrade the surface and then clean with Desoclean™ 110 solvent cleaner.

## Instructions for Use



### Mixing Instructions:

Prior to mixing, thoroughly shake the base component. Add the activator to the base component and stir well. Maintain constant agitation for 10 minutes to ensure proper mixing.

*Note: It is important to condition the paint for 24 hours prior to mixing by placing all materials in the shop or hangar, with ambient temperatures between 13° and 35°C (55° to 95°F). The minimum temperature of the paint components should be 13°C (55°F) prior to mixing.*



### Induction Time:


Not Required



### Viscosity: (23°C/73°F)

• #1 Zahn cup	49 seconds maximum
• #2 Zahn cup	25 seconds maximum
• #4 Ford cup	22 seconds maximum
• !SO 3	64 seconds maximum
• ISO 4	30 seconds maximum
• BSB3 cup	22 seconds maximum
• BSB4 Cup	20 seconds maximum
• AFNOR # 2.5 cup	66 seconds maximum
• AFNOR #4 cup	19 seconds maximum

*Note: Viscosities quoted are typical values obtained when using specified mix ratio.*



### Pot Life:

Whites and grays 3 hours @ 21 - 25°C (70 - 77°F)  
All other colors 2 hours @ 21 - 25°C (70 - 77°F)

# Desothane<sup>®</sup> HS CA8100 Series Military and Defense Anti-Chafe Topcoats

## Application Guidelines

### Recommended Application Conditions:

Temperature	15 - 30°C (59 - 86°F)
Relative Humidity	20 - 90%

### Application:


Ground the aircraft and the application equipment before top coating. Stir the topcoat slowly during the application. The suggested film thickness is 125 to 250 microns (5 to 10 mils). This can be accomplished by spraying three or four coats of anti-chafe coating. The previous coat should be allowed to tack up before applying the next coat. If rolling instead of spraying, apply the next coat after the previous coat has tacked up.

*These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment, and other variables.*



### Theoretical Coverage:

22 square meters/liter at 25 microns dry film (850 square feet/gallon at 1 mil dry film)  
Recommended dry film thickness; 125 to 250 microns (5 to 10 mils)



### Dry Film Density

1.56 grams/cubic centimeter (13.0 pounds/gallon)

### Dry Film Weight:

39 grams/square meter at 25 microns dry film (0.0070 pounds/square feet at 1 mil dry film)

# Desothane<sup>®</sup> HS CA8100 Series Military and Defense Anti-Chafe Topcoats


**Equipment:**

CA8100 series topcoats are compatible with all current forms of spray equipment.

Equipment Type	Tip Size	Pot Pressure	Atomization Pressure at the Cap
Electrostatic Air Spray Gun	1.2 mm or 1.5 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)
Electrostatic Air Assisted Airless Spray Gun	#611 or #613 (Graco Nomenclature)	700 to 1200 psi (48 to 82 bar)	40 to 60 psi (2.8 to 4.1 bar)
High Volume Low Pressure Spray Gun (HVLP)	1.0 mm to 1.4 mm	10 to 20 psi (0.69 to 1.4 bar)	10 psi maximum (0.69 bar)
Conventional Air Spray Gun	1.2 mm to 1.8 mm	10 to 20 psi (0.69 to 1.4 bar)	45 to 60 psi (3.1 to 4.1 bar)

**Equipment Cleaning:**

Clean spray equipment as soon as possible after use. Flush spray equipment with DeSoto<sup>®</sup> CN20, DeSoto<sup>®</sup> CN44, or Desoclean<sup>™</sup> 45 high performance solvent cleaner.

## Physical Properties (product)



**Color:** Can be matched to any color standard



**Gloss:** 70 G.U at 60°



Dry Times	13 - 21°C (55 - 70°F)	22 - 28°C (71 - 84°F)	>29°C (>85°F)
Dry Hard	11 hours	10 hours	9 hours
Dry to Fly	65 hours	48 hours	38 hours
Full Cure	7 days	7 days	7 days

Accelerated cure for dry hard:

Allow 30 minutes flash off at 24°C ± 3°C (75°F ± 10°F)  
followed by 60 minutes at 49°C (120°F)

*Note: Faster drying version also available.*

# Desothane<sup>®</sup> HS CA8100 Series Military and Defense Anti-Chafe Topcoats



**VOC:**

Mixed, ready to use VOC (EPA method 24)

Base Component 289 grams/liter

Activator Component 423 grams/liter



**Flash point closed cup:**

Base Component 27°C (80°F)

Activator Component 27°C (80°F)

**Shelf Life:**


12 months from date of manufacture to most OEM material specifications. Consult the specification to verify shelf life requirements.

24 months from date of manufacture for PRC-DeSoto Standard.

*Note: Shelf life is provided for original, unopened containers.*

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## Storage Recommendations



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*

# Desothane<sup>®</sup> HS CA8100 Series Military and Defense Anti-Chafe Topcoats

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC – South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

Desoclean, Desoprime, Desothane, and DeSoto are trademarks of PRC-DeSoto International, Inc.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PRC-DeSoto International, Inc.

12780 San Fernando Road  
Sylmar, CA 91342

[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 7/16  
Lit: 0547