


## Celoflex™ 95 Erosion Resistant Polyurethane Topcoat

### Product Description

Celoflex™ 95 is a polyurethane topcoat designed to provide erosion resistance on radomes and leading edges. Celoflex™ 95 is intended for use on non-metallic / metallic parts and areas exposed to rain erosion.

- Excellent fluid and erosion resistance
- Conventional solids
- Excellent UV resistance

### Components



#### Mix Ratio (by volume)

- 5478/.... (Base) 1 part
- 0778/9000 (Activator) 1 part
- 0470/9000 (Thinner) 0.5 - 1 part

### Specifications



5478/.... is qualified to:

- AIMS 04-04-016

5478/.... is compatible with the following primer / topcoat specifications:

- AIMS 04-04-005
- AIMS 04-04-012
- AIMS 04-04-013
- AIMS 04-04-031
- AIMS 04-04-032
- BAMS 565-09
- BLGG 140301
- BMS 10-60
- BMS 10-72
- BS2X34B
- DHMS C4.04

*Note: PPG Aerospace recommends you check the most recent specification QPLs for updated information.*

# Celoflex™ 95 Erosion Resistant Polyurethane Topcoat

## Surface Preparation and Pretreatment



Apply over a suitably prepared primer/surfacer. Ensure surface is clean, dry and intact using a high performance solvent cleaner. DeSoto® CN20 or Desoclean™ 45 solvent cleaners are recommended. Observe recommended overcoating windows.

## Instructions for Use



Before adding the activator to the base, thoroughly stir or shake the base component until a smooth uniform mix is obtained. Immediately after adding the activator to the base, stir thoroughly then add required thinner while stirring.

*Note: all products and components should be placed in ambient conditions of 15-30°C (59-86°F) for at least 24 hours prior to mixing and application.*



### **Induction Time:**


Not required



### **Viscosity:** ( 23°C/73°F)

• AFNOR4	15 - 21 seconds
• BSB3	31 - 42 seconds
• FORD4	11 - 17 seconds
• ISO4	25 - 40 seconds
• ZAHN2	21 - 28 seconds

*Note: Viscosities quoted are typical ranges obtained when using specified mix ratio.*



### **Pot Life:**

3 hours @ 21 - 25°C (70 - 77°F)

# Celoflex™ 95 Erosion Resistant Polyurethane Topcoat

## Application Guidelines

### Recommended Application Conditions:

Temperature 15 - 30°C (59 - 86°F)  
Relative Humidity 30 - 80%

### Application:

Apply 2 or 3 coats. Wait 30 minutes between coats.




### Theoretical Coverage: (ready for use)

3 m<sup>2</sup>/Lt @ 100 µm dry film thickness  
120 ft<sup>2</sup>/US gal @ 4 mil dry film thickness

### Recommended Dry Film Thickness:

80 - 120 µm  
3.2 - 4.8 mil



### Dry Film Density:

1.26 g/cm<sup>3</sup>  
10.4 lbs/US gal

### Dry Film Weight: (mix ratio 1:1:1)

126 g/m<sup>2</sup> @ 100 µm dry film thickness  
0.025lbs/ft<sup>2</sup> @ 4 mil dry film thickness

*Note: These application guidelines represent PPG's best advice for usage in standard conditions. Some parameters will be influenced by environmental conditions, equipment settings, and other variables.*

### Equipment:



Equipment Type	Tip Size (mm)	Pressure
Conventional Air Spray	1.5 to 1.8	43 to 72 psi (3 to 5 bar)

### Equipment Cleaning:

Clean spray equipment before use and as soon as possible after use. DeSoto® CN20, CN44 or Desoclean™ 45 solvent cleaners are recommended.

# Celoflex™ 95 Erosion Resistant Polyurethane Topcoat

## Physical Properties



### Colour:

White (5478/0000)  
Brilliant Dark Grey/Blue (5478/2723)  
Medium Blue/Light Grey (5478/2182)  
Black (5478/2909)




### Gloss:

>90 units with a 60° gloss meter



Drying Times @ 50% R.H	@ 23°C (73°F)	@ 80°C (176°F)
Dry to Handle	4 hours	90 minutes
Dry to Tape	12 hours	-
Dry to Overcoat	4 to 24 hours	-
Full Cure	7 days	3 to 4 hours

*Note: Drying times listed above are dependent upon film thickness applied, air flow conditions and application technique.*



### Flash Off Time:

30 minutes @ 23°C (73°F) prior to force drying @ 80°C (176°F)



### VOC: (ASTM)

Mixed (1:1:1) ready for use 550 g/Lt  
5478/0000 Base Component 180 g/Lt  
0778/9000 Activator 620 g/Lt  
0470/9000 Thinner 850 g/Lt



### Flash Point:

5478/0000 Base Component 2°C (36°F)  
0778/9000 Activator 23°C (73°F)  
0470/9000 Thinner 1°C (34°F)

### Shelf Life:

5478/0000 Base Component 12 months in original unopened container  
0778/9000 Activator 12 months in original unopened container  
0470/9000 Thinner 10 years in original unopened container

*Note: Shelf life may vary due to OEM specification requirements. Refer to container label for specific shelf life information.*

# Celoflex™ 95 Erosion Resistant Polyurethane Topcoat

*Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.*

## **Storage Recommendations**



Inspect the condition of the container to ensure compliance. The material should be stored at temperatures between 5°C to 35°C (41°F to 95°F) to ensure shelf life.

*Note: When procuring to a qualified material specification, follow those storage instructions.*

# Celoflex™ 95 Erosion Resistant Polyurethane Topcoat

## Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Safety Data Sheet (SDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An SDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**Additional information can be found at: [www.ppgaerospace.com](http://www.ppgaerospace.com)**

**For sales and ordering information call the local PPG office at the numbers listed below:**

### **Asia Pacific**

#### **ASC – Australia**

Tel 61 (3) 9335 1557  
Fax 61 (3) 9335 3490

#### **ASC – Japan**

Tel 81 561 35 5200  
Fax 81 561 35 5201

#### **ASC – South East Asia**

Tel 65 6861 1119  
Fax 65 6861 6162

#### **ASC – Suzhou**

Tel (86-512) 6661 5858  
Fax (86-512) 6661 6868

#### **ASC – Tianjin**

Tel (86-022) 2482 8625  
Fax (86-022) 2482 8600

### **Europe and Middle East**

#### **ASC – Central Europe**

Tel 49 (40) 742 193 10  
Fax 49 (40) 742 139 69

#### **ASC – Middle East & India**

Tel (971) 4 883 9666  
Fax (971) 4 883 9665

#### **ASC – North Europe**

Tel 44 (0) 1388 770222  
Fax 44 (0) 1388 770288

#### **ASC – South Europe**

Tel 33 (0) 235 53 43 71  
Fax 33 (0) 235 53 54 44

### **Americas**

1 (818) 362-6711 or 1-800-AEROMIX

**Celoflex, Desoclean, and DeSoto are trademarks of PRC-DeSoto International, Inc.**

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

PPG Aerospace

Sealants and Coatings

Darlington Road

Shildon, Co Durham UK

DL4 2QP

[www.ppgaerospace.com](http://www.ppgaerospace.com)

Issue Date: 11/18

Lit: 4262